

Admonter Wooden acoustic panels Acoustics GEO Accompanying information** to CE-marking according to EN 13964

		Reaction to fire*	Emission of formaldehyde EN 717-2	Content of pentachlorophenol	Flexural tensile strength	Bondstrength	Sound absorption α_w	Thermal conductivity***) λ_D [W/m K]	Durability according to EN 335
Type 16-16/12	Structure 1	D-s2,d0	E1	≤ 5 ppm	Class A no load	NPD	0,70	0,041	Class 1
	Structure 2						0,65 (H)	0,041	
	Structure 2 a						0,65 (H)	0,041	
	Structure 3						0,60 (H)	0,041	
Type 15-30/09	Structure 1	D-s2,d0	E1	≤ 5 ppm	Class A no load	NPD	0,65	0,041	Class 1
	Structure 2						0,60 (H)	0,041	
	Structure 2 a						0,60 (H)	0,041	
	Structure 3						0,60 (H)	0,041	
Type 20-40/07	Structure 1	D-s2,d0	E1	≤ 5 ppm	Class A no load	NPD	0,60	0,041	Class 1
	Structure 2						0,60	0,041	
	Structure 2 a						0,60	0,041	
	Structure 3						0,55 (MH)	0,041	

*) Notes concerning reaction to fire: tested and classified according to EN 13501-1. Only valid with factory surface, mechanical attachment.

**) Valid for: Spruce, Larch, Fir rift/halbrift finger-jointed

***) Based on 15 mm soft fiber core, excluding on-site cavity damping

Admont, September 2023

Wooden Floors
Floors

Wooden Panels
Elements

Wooden acoustic panels
Acoustics

Wooden Stairs
Stairs

Wooden Doors
Doors

Admonter Holzindustrie AG

Sägestraße 539 | 8911 Admont, Austria
+43 (0) 3613 3350 | info@admonter.at

FN237499p Landesgericht Leoben, Gerichtsstand Liezen | UID-Nr.: ATU57198366
Raiffeisenbank Admont, IBAN: AT88 3800 1000 0002 7276 | BIC: RZSTAT213001